

P3 Deflect™ 120



INFINAM® 

An Evonik product.

High-temperature photopolymer with good strength for functional parts, from Evonik INFINAM®.

Our first photopolymer from Evonik is a strong, heat-resistant material that addresses applications where a combination of high-temperature resistance and good elongation at break are crucial. P3 Deflect 120 has low viscosity and high green strength, which make it suitable for parts with challenging geometries such as wiring housings, connectors, or mold tooling.

Key Benefits

- High HDT, 121°C (250°F) with good elongation at break
- Very stiff and high green strength
- Easy to print + single component material
- Color: Black



	Unit	Value	Method
MECHANICAL PROPERTIES			
Ultimate Tensile Strength	MPa	100	ASTM D638
Young Modulus	MPa	3000	ASTM D638
Elongation at Break	%	4	ASTM D638
Flexural Modulus	MPa	3715	ASTM D790
Flexural Stress at 5% Strain	MPa	132	ASTM D790
Izod Notched Impact Strength	J/m	15	ASTM D256
THERMAL PROPERTIES			
Heat Deflection Temperature (0.455 MPa)	°C	121	ASTM D648
PHYSICAL PROPERTIES			
Ec / Dp	mJ/cm ² / mm	3.48 / 0.12	Internal
Shore Hardness (3s)	-	88	ASTM D2240
Liquid Viscosity at 25°C	mPa · s	450	ASTM D7867

Stratasys Headquarters

7665 Commerce Way,
Eden Prairie, MN 55344
+1 800 801 6491 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

1 Holtzman St., Science Park,
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000
+972 74 745 5000 (Fax)

stratasys.com

ISO 9001:2015 Certified

© 2023 Stratasys. All rights reserved. Stratasys and the Stratasys Signet logo are registered trademarks of Stratasys Inc. PolyJet, J735, J750, J826, J835, J850, J4100, VeroUltraClear, VeroClear, SUP705 and SUP706B are trademarks of Stratasys, Inc. All other trademarks are the property of their respective owners, and Stratasys assumes no responsibility with regard to the selection, performance, or use of these non-Stratasys products. Product specifications subject to change without notice. MDS_P3_DURA56 Deflect 120_0123a

